

AMENDMENTS TO THE SPECIFICATION:

Please add the following heading on page 19, after line 7 and before line 8:

BRIEF DESCRIPTION OF THE DRAWINGS

Please amend the paragraph on page 31 beginning on line 26 as follows:

Propylene polymerisation using catalysts (H) - (J) were carried out in a 2 litre reactor. Dry catalyst was introduced into the reactor under nitrogen purging, whereafter ~~polypropylene~~ propylene (650 ml) was added. After 8 minutes prepolymerisation at 15°C the temperature was rapidly raised to 70°. The polymerisation time was 60 minutes.

Results are shown in the following Table 4: